


PN2 Aerospace Grade Aramid Fiber Honeycomb



Description:

PN2 aerospace grade aramid fiber honeycomb exhibits outstanding flammability properties. It is manufactured from DuPont Nomex® paper (or equivalent) and coated with a heat resistant phenolic resin.

Applications:

PN2 honeycomb uses include aircraft galleys, flooring, partitions, aircraft leading and trailing edges, missile wings, radomes, antennas, military shelters, fuel tanks, helicopter rotor blades and navy bulkhead joiner panels.

Features:

- Fire resistant (self extinguishing)
- High strength to weight ratio
- Corrosion resistant
- Excellent dielectric properties
- Thermally insulating
- High toughness
- Excellent creep and fatigue performance
- Good thermal stability
- Densities as low as 1.5 lb/ft³ (24 kg/m³)
- Over expanded cell configuration suitable for forming simple curves
- Compatible with most adhesives used in sandwich composites

Availability:

PN2 honeycomb is available in sheets, blocks or cut to size pieces in both regular hexagonal and over expanded (OV) cell configurations.

Cell Sizes: 1/8" - 1/4"

Densities: 1.8 pcf - 9.0 pcf

Sheet "Ribbon" (L): 48" typical

Sheet "Transverse" (W): 96" typical

Tolerances:


Length:	+ 3", - 0" (36" for OV)
Width:	+ 6", - 0"
Thickness:	± .006" (under 2" thick)
Density:	± 10%
Cell Size:	± 10%

NOTE: Special dimensions, sizes, tolerances and specifications can be provided upon request.

PN2 aerospace grade aramid fiber honeycomb is specified as follows:

Material - Cell Size - Density - Cell Configuration

Note: 1/8" OV core can be over expanded only to a maximum of 20% over nominal cell size.
 ©Nomex is a registered trademark of E.I. DuPont de Nemours, Wilmington, Delaware.



PN2 Mechanical Properties																		
PLASCORE® Honeycomb Designation	DENSITY		COMPRESSIVE (BARE)				PLATE SHEAR "L" DIRECTION				PLATE SHEAR "W" DIRECTION							
			STRENGTH (psi/MPa)				STRENGTH (psi/MPa)				MODULUS (ksi/GPa)		STRENGTH (psi/MPa)				MODULUS (ksi/GPa)	
			TYP		MIN		TYP		MIN		TYP		TYP		MIN		TYP	
	lb/ft³	kg/m³	psi	MPa	psi	MPa	psi	MPa	psi	MPa	ksi	GPa	psi	MPa	psi	MPa	ksi	GPa
PN2-1/8-1.8	1.8	29	85	0.59	74	0.51	75	0.52	60	0.41	3.8	0.026	45	0.31	32	0.22	1.7	0.012
PN2-1/8-3.0	3.0	48	290	2.00	200	1.38	205	1.41	140	0.97	6.7	0.046	105	0.72	74	0.51	3.5	0.024
PN2-1/8-4.0	4.0	64	515	3.55	350	2.41	275	1.90	215	1.48	8.6	0.059	150	1.04	108	0.74	4.7	0.032
PN2-1/8-5.0	5.0	80	700	4.83	540	3.72	325	2.24	265	1.83	10.8	0.074	215	1.48	130	0.90	6.2	0.042
PN2-1/8-6.0	6.0	96	930	6.41	700	4.83	360	2.48	320	2.21	12.9	0.089	245	1.69	150	1.03	7.5	0.052
PN2-1/8-8.0	8.0	128	1700	11.72	1170	8.07	420	2.90	400	2.76	16.7	0.115	295	2.03	200	1.38	10.6	0.073
PN2-1/8-9.0	9.0	144	2145	14.79	1450	10.00	445	3.07	425	2.93	18.7	0.129	315	2.17	240	1.65	11.2	0.077
PN2-3/16-1.8	1.8	29	90	0.62	74	0.51	70	0.48	50	0.34	3.3	0.023	45	0.31	30	0.21	1.8	0.013
PN2-3/16-2.0	2.0	32	125	0.86	93	0.64	95	0.66	70	0.48	4.5	0.031	55	0.38	40	0.28	2.5	0.017
PN2-3/16-3.0	3.0	48	300	2.07	200	1.38	185	1.28	140	0.97	6.1	0.042	110	0.76	67	0.46	4.1	0.028
PN2-3/16-4.0	4.0	64	515	3.55	350	2.41	235	1.62	215	1.48	8.2	0.056	165	1.14	112	0.77	5.5	0.038
PN2-1/4-1.5	1.5	24	70	0.48	54	0.37	55	0.38	45	0.31	2.8	0.019	35	0.24	23	0.16	1.7	0.012
PN2-1/4-2.0	2.0	32	130	0.90	93	0.64	90	0.62	70	0.48	3.8	0.026	55	0.38	36	0.25	2.4	0.017
PN2-1/8-3.0-OV	3.0	48	270	1.86	200	1.38	165	1.14	100	0.69	5.0	0.035	115	0.79	80	0.55	4.0	0.027
PN2-3/16-1.8-OV	1.8	29	95	0.66	75	0.52	60	0.41	35	0.24	2.2	0.015	60	0.41	36	0.25	3.3	0.023
PN2-3/16-2.0-OV	2.0	32	115	0.79	90	0.62	70	0.48	50	0.34	2.4	0.016	70	0.48	40	0.28	3.9	0.027
PN2-3/16-3.0-OV	3.0	48	280	1.93	250	1.72	115	0.79	75	0.52	3.3	0.023	135	0.93	75	0.52	6.6	0.045
PN2-3/16-4.0-OV	4.0	64	495	3.41	350	2.41	160	1.10	100	0.69	4.1	0.028	195	1.34	120	0.83	9.4	0.065
PN2-3/8-3.0-OV	3.0	48	250	1.72	200	1.38	105	0.72	60	0.41	2.8	0.020	135	0.93	80	0.55	6.5	0.045

NOTE: The above data is based on variable sample sizes and is subject to change with continued manufacturing and testing of PN2 honeycomb core blocks per MIL-C-81986 at room temperature.

Plascore, Inc., employs a quality management system that is AS/EN/JISQ 9100, ISO 9001:2008 and ISO 14001:2004 certified.

IMPORTANT NOTICE: The information contained in these materials regarding Plascore's products, processes, or equipment, is intended to be up to date, accurate, and complete. However, Plascore cannot warrant that this is always the case. Accordingly, it is a purchaser's or user's responsibility to perform sufficient testing and evaluation to determine the suitability of Plascore's products for a particular purpose. Information in these materials and product specifications does not constitute an offer to sell. Your submission of an order to Plascore constitutes an offer to purchase which, if accepted by Plascore, shall be subject to Plascore's terms and conditions of sale. **PLASCORE MAKES NO WARRANTIES OF ANY KIND REGARDING THESE MATERIALS OR INFORMATION, EITHER EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Plascore owns and shall retain all worldwide rights in its intellectual property, and any other trademarks used in these materials are the property of their respective owners. The information in these materials shall not be construed as an inducement, permission, or recommendation to infringe any patent or other intellectual property rights of any third parties.



Corporate Headquarters

Plascore Incorporated
 615 N. Fairview St.
 Zeeland, MI 49464-0170
 Phone (616) 772-1220
 Toll Free (800) 630-9257
 Fax (616) 772-1289
 Email sales@plascore.com
 Web www.plascore.com

Europe

Plascore GmbH&CoKG
 Feldborn 6
 D-55444 Waldlaubersheim
 Germany
 Phone +49(0) 6707-9143 13
 Fax +49(0) 6707-9143 40
 Email sales.europe@plascore.com
 Web www.plascore.de